


**DI-ISOPENTYL TEREPHTHALATE**

The structure is simplified and shows only one of several isomers contained in the product.

**REGULATORY INFORMATION**

CAS no. 2097734-13-7  
REACH no. 01-2120126889-41-0000

**APPLICATIONS & PROPERTIES**

**ELATUR<sup>®</sup> DPT is a fast fusing, low-viscosity plasticizer with a very good emission profile.**

**PRODUCT SPECIFIC FEATURE**

Effective fast fuser especially in combination with ELATUR<sup>®</sup> CH (DINCH). ELATUR<sup>®</sup> DPT contains < 1 % SVOC components.<sup>1)</sup>

**APPLICATION FIELDS**

- Preferred use in PVC plastisols
- Manufacturing and processing of PVC dryblends
- Flexibilization of paints, varnishes, and adhesives

**TRANSPORT & LOGISTICS**

Delivery in tank trucks and ISO containers

**SPECIFICATION**

Property	Value	Unit	Method
Color (Pt-Co)	max. 30	mg Pt/l	DIN EN ISO 6271
Acid number	max. 0.05	mg KOH/g	DIN EN ISO 2114
Ester content	min. 99.0	area %	Evonik, GC <sup>3)</sup>
Water	max. 0.1	mass %	DIN 51 777
Low-boiling components	max. 1	area %	Evonik, GC <sup>3)</sup>
o-phthalate content <sup>2)</sup>	max. 0.01	mol %	Evonik, NMR <sup>3)</sup>

<sup>1)</sup> SVOC: semi-volatile organic compounds; based on DIN EN 16516 and DIN EN 16000-6 (modified)

<sup>2)</sup> checked regularly but not batchwise <sup>3)</sup> in-house method

## LITERATURE AND TYPICAL DATA

Property	Value	Unit	Method
Appearance	Clear liquid		visual inspection
Molar mass	306	g/mol	
Dynamic viscosity, 20 °C	32	mPa s	DIN EN ISO 3104
Refractive index, 20 °C	1.4943		DIN 51 423/2
Solution temperature (S-PVC, K value 82)	115	°C	video-based analysis <sup>4)</sup>

<sup>4)</sup> in-house method

### Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

**Evonik Oxeno GmbH & Co. KG**  
Paul-Baumann-Straße 1  
45772 Marl  
C4-chemicals@evonik.com  
[www.evonik.com/c4-chemicals](http://www.evonik.com/c4-chemicals)