

Application information

TMT 15[®] - THE RESISTANCE OF MATERIALS TO TMT 15[®]

INFO 9 E

To ensure safe handling, storage and transport of the heavy metal precipitation agent TMT 15[®], suitable alkali-resistant materials must be used. The following tables provide an overview of the chemical resistance of conventional commercial materials and sealants to TMT 15[®].

Corrosion and immersion tests were carried out in the laboratory on immersed samples at 20–50 °C over a test period of 25 - 40 days. The parameters measured included weight change, swelling, hardness, visual changes, strength characteristics and erosion, depending on the type of material tested.

TEST MEDIUM

TMT 15 [®]	(Trimercapto-s-triazine, trisodium salt) 15 % aqueous solution
CAS-RN	17766-26-6
pH value	12.5
Density	1.12 g/cm ³

CLASSIFICATION

+ (resistant)	The material is not influenced, or is influenced only to a very small degree, by pressure or temperature within the permitted limits.
o (limited resistant)	The material is attacked or its properties altered. The life of the material can be noticeably reduced. Enquiry is recommended
- (not resistant)	The material cannot be used or can be used only under special circumstances. Enquiry is essential

The information is intended as an aid to an orientation for the selection of suitable materials to be used with TMT 15[®]. Changes in the composition of the medium or special operational conditions can result in variations.

1. PLASTICS

Material		Commercial product	Resistance
Polyethylene	PE-HD	Hostalen GM 5010 T2 (Hoechst AG)	+
Polyvinylchloride	PVC-U	TROVIDUR EN (Hüls Troisdorf AG)	+
Polypropylene	PP	TROVIDUR EN (Hüls Troisdorf AG)	+
Unsaturated polyester resin, glass-fibre reinforced	UP-GF	PALATAL A 410 (BASF)	+

The resistance of glass-fibre reinforced epoxy resin (EP-GF) was not investigated separately. Because of the good alkaline resistance of epoxy resins, their chemical resistance to TMT 15[®] can be assumed.

2. SEALANTS

Material		Commercial product	Resistance
Nitrile rubber	NBR	Quality N (Wavin)	+
Ethylene propylenediene terpolymer	EPDM	Quality E (Wavin)	+
E/A copolymer (polyethylene Copolymer)		Lucalen A 2710 H (BASF)	+
Fluoroelastomer	FPM	Viton (Du Pont)	+
Polyvinyl chloride (soft)	PVC-P	Mipolam	0
Silicone rubber	VQM	Vicarb 055	+
Aramid fibre gasket *		Klinger Sil C 4400 (Klinger)	0
Aramid fibre gasket *	UP-GF	Novapress 300 (Frenzelit)	-

* As flat sealant material, Aramid/NBR gaskets with a PTFE sheath are suitable
The resistance of PTFE (polytetrafluoroethylene), such as Teflon (Du Pont), was not investigated.
Based on available data from the literature, chemical resistance to TMT 15[®] can be assumed.

3. METALLIC MATERIALS

Material		Commercial product	Resistance
Non-alloy steel Boiler plate H11		W.-Nr. 1.0425	0
Stainless steel	Type 304	W.-Nr. 1.4541	+
Stainless steel	Type 316	W.-Nr. 1.4571	+

The resistance of non-ferrous metals such as zinc and copper was not investigated. For these metals, as also for aluminium, it can be assumed that they are not resistant or have only limited chemical resistance to TMT 15[®].

Disclaimer

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Sales & Marketing
Evonik Performance Materials GmbH
Paul-Baumann-Straße 1
45772 Marl, Germany
PHONE: +49 2365 49 7653
tmt@evonik.com
www.tmt15.com

Applied Technology
Evonik Performance Materials GmbH
Rodenbacher Chaussee 4
63457 Hanau, Germany
PHONE: +49 6181 59-2854
tmt@evonik.com
www.tmt15.com

